

(19)  **Canadian
Intellectual Property
Office**

An Agency of
Industry Canada

**Office de la Propriété
Intellectuelle
du Canada**

Un organisme
d'Industrie Canada

(11) **CA 2 238 928**

(13) **C**

(40) **17.06.2003**

(43) **29.11.1998**

(45) **17.06.2003**

(12)

(21) **2 238 928**

(51) Int. Cl. ⁶:

B22D 1/00, C21C 7/00,

B22D 41/02, C22B 9/10

(22) **28.05.1998**

(30) **60/047,893 US 29.05.1997**

(72)

VAYDA, PIERRE (CA).

(73)

**EXOTHERMIC DISTRIBUTION CORPORATION
4962 Union Road Unit #2 BEAMSVILLE O1 (CA).**

(74)

SIM & MCBURNEY

(54) **UTILISATIONS DE L'ALUMINATE DE STRONTIUM DANS L'ELABORATION DE L'ACIER**

(54) **UTILIZATION OF STRONTIUM ALUMINATE IN STEELMAKING**

(57)

Novel utilizations of strontium aluminate, a by-product of the manufacture of strontium, are disclosed in connection with the art of steelmaking. It is useful as a synthetic slag covering for molten iron or steel, as well as in the foaming slag practice, as a backfilling material for spaces between the safety lining and the working lining of a ladle, as a major component for a blend from which are made pellets or briquettes useful as a slag conditioner, as an additive to calcium aluminate which has the effect of substantially lowering the melting point of calcium aluminate, as a tracer material to determine the source of impurities, and as a binder to recycle metal-containing dust.



Office de la Propriété
Intellectuelle
du Canada

Un organisme
d'Industrie Canada

Canadian
Intellectual Property
Office

An agency of
Industry Canada

CA 2238928 C 2003/06/17

(11)(21) **2 238 928**

(12) **BREVET CANADIEN
CANADIAN PATENT**

(13) **C**

(22) Date de dépôt/Filing Date: 1998/05/28

(41) Mise à la disp. pub./Open to Public Insp.: 1998/11/29

(45) Date de délivrance/Issue Date: 2003/06/17

(30) Priorité/Priority: 1997/05/29 (60/047,893) US

(51) Cl.Int.⁶/Int.Cl.⁶ B22D 1/00, B22D 41/02, C22B 9/10,
C21C 7/00

(72) Inventeur/Inventor:
VAYDA, PIERRE, CA

(73) Propriétaire/Owner:
EXOTHERMIC DISTRIBUTION CORPORATION, CA

(74) Agent: SIM & MCBURNEY

(54) Titre : UTILISATIONS DE L'ALUMINATE DE STRONTIUM DANS L'ELABORATION DE L'ACIER
(54) Title: UTILIZATION OF STRONTIUM ALUMINATE IN STEELMAKING

(57) **Abrégé/Abstract**

Novel utilizations of strontium aluminate, a by-product of the manufacture of strontium, are disclosed in connection with the art of steelmaking. It is useful as a synthetic slag covering for molten iron or steel, as well as in the foaming slag practice, as a backfilling material for spaces between the safety lining and the working lining of a ladle, as a major component for a blend from which are made pellets or briquettes useful as a slag conditioner, as an additive to calcium aluminate which has the effect of substantially lowering the melting point of calcium aluminate, as a tracer material to determine the source of impurities, and as a binder to recycle metal-containing dust.

Canada

<http://opic.gc.ca> • Ottawa-Hull K1A 0C9 • <http://cipo.gc.ca>

OPIC • CIPO 191

OPIC



CIPO

ABSTRACT OF THE DISCLOSURE

Novel utilizations of strontium aluminate, a by-product of the
5 manufacture of strontium, are disclosed in connection with the art of
steelmaking. It is useful as a synthetic slag covering for molten iron or steel,
as well as in the foaming slag practice, as a backfilling material for spaces
between the safety lining and the working lining of a ladle, as a major
component for a blend from which are made pellets or briquettes useful as a
10 slag conditioner, as an additive to calcium aluminate which has the effect of
substantially lowering the melting point of calcium aluminate, as a tracer
material to determine the source of impurities, and as a binder to recycle
metal-containing dust.

15

UTILIZATION OF STRONTIUM ALUMINATE IN STEELMAKING

This invention relates generally to the art of steelmaking, and has to do particularly with the previously unknown use of strontium aluminate in steelmaking.

5

BACKGROUND OF THIS INVENTION

The metal strontium is normally obtained by using aluminum to reduce strontium oxide. Prior to the present invention, the by-product of the strontium manufacturing process, strontium aluminate, has been considered to be without any
10 important use, and as a result large quantities of strontium aluminate are stockpiled every year.

Strontium aluminate is a basic, alumina-saturated, highly refractory product. It is not radio-active because it is generated by the reduction of the naturally occurring strontium carbonate. Radio-active strontium oxide is that generated by nuclear
15 fusion.

GENERAL DESCRIPTION OF THIS INVENTION

In accordance with the present invention, it has been found that the strontium aluminate by-product can be used with considerable advantage in various facets of the
20 steelmaking process.

The various facets are as follows:

In accordance with one embodiment, there is provided a method of insulating and protecting a molten metal in a ladle, the method consisting of distributing over the surface of the molten metal a material which includes strontium aluminate.

25 The molten metal may be one selected from the group consisting of: iron; steel; aluminium.

In accordance with another aspect, there is provided, in the handling of molten metal in a ladle which has both a safety lining and a working lining, a method of maintaining the ladle by backfilling any space between the two linings with a material
30 which includes strontium aluminate.

A further aspect of this invention involves the use of the cementitious characteristic of strontium aluminate, acting as a major component of a blend from which are made pellets or briquettes useful as a slag conditioner, particularly in the art of steelmaking.

5 Another aspect of this invention involves the use of strontium aluminate as a tracer material, in order to determine the source of contamination.

Furthermore, strontium aluminate can be used to briquette metal-containing dust, so that it can be recycled.

10 Finally, there is provided a method of lowering the melting point of calcium aluminate by from about 50 to about 75°, the method consisting of adding from about 5 to about 15% by weight of strontium aluminate thereto.

DETAILED DESCRIPTION OF THE INVENTION

15 It has been found that strontium aluminate, either alone or blended with other materials, can be used in ladles and tundishes to provide a protective and insulative synthetic slag covering for molten iron or steel. Not only does the strontium aluminate provide good insulating properties, but it also is neutral to either basic lining or alumina lining, these making up most of the linings currently used for ladles in the art of steelmaking.

20 In a particular embodiment, the strontium aluminate can be blended with other compounds, particularly silico-aluminate, when the blend is to be used as a slag cover in a ladle or a tundish.

25 In another aspect, strontium aluminate is useful for maintaining the integrity of a steelmaking ladle which has both a safety lining and a working lining. This method consists of backfilling any space between the two linings with a material which includes strontium aluminate. The backfill material may be either strontium aluminate by itself, or a blend of strontium aluminate with magnesia or alumina.

According to a further embodiment, strontium aluminate can be used as a major component of a blend from which are made pellets or briquettes useful as a slag conditioner, particularly for the art of steelmaking. In one particular example, not to be considered limiting, a blend for pellets or briquettes may contain about 60% by weight of strontium aluminate, about 20% by weight of aluminum granules, and the rest water. The blend of material is placed into appropriate molds, and is allowed to cure at room temperature for about 24 hours. Experiment has indicated that the process just described results in pellets or briquettes with good structural integrity and excellent resistance to crumbling or returning to powder form.

In connection with the use of strontium oxide as a tracer for contamination, the following example can be given:

- a) Alumina impurities in cast steel could originate from the refractory, the ladle slag or the tundish slag. By adding strontium aluminate to a suspected source of contamination, for instance the ladle slag, the finding of strontium aluminate in the cast steel will indicate that the alumina contamination comes from the ladle slag;
- b) As mentioned it is possible to recycle metal-containing dust (such as electric furnace flue dust which contains a high percentage of iron oxide), so that it can be recycled into the furnace that generated it or to a plasma furnace to recuperate the metals (nickel, copper, chrome). Generally speaking, it is not possible to add fines into a melting furnace, as they tend to be sucked directly into the dust collector system from which they originally came. The only viable method is to bind the dust into a briquette or the like, so that it can be introduced into the melt efficiently. The lining in a furnace is usually basic, made of either magnesite or dolomite brick. It can also be made out of alumina brick. It is desirable, of course, to use a binder compatible with the furnace lining, since this will reduce lining erosion due to the slag formed during a melt. Hence, strontium aluminate becomes an excellent candidate as a binder, since it is basic and saturated with alumina, and will not attack the lining.

The final embodiment involves the lowering of the melting point of calcium aluminate by from about 50° to 75°, the method consisting of adding from about 5% to 15% by weight of strontium aluminate thereto.

5 While several embodiments of this invention have been described above, it will be evident to those skilled in the art that changes and modifications may be made thereto without departing from the essence of this invention, as set forth in the appended claims.

THE EMBODIMENTS OF THE INVENTION IN WHICH AN EXCLUSIVE
PROPERTY OR PRIVILEGE IS CLAIMED ARE DEFINED AS FOLLOWS:

1. A method of insulating and protecting a molten metal in a ladle, the method
5 consisting of distributing over the surface of the molten metal a material which
includes strontium aluminate.
2. The method claimed in claim 1, in which the said material consists
substantially solely of strontium aluminate.
- 10 3. The method claimed in claim 1, in which the molten metal is selected from the
group consisting of: iron; steel; aluminum.
4. The method claimed in claim 2, in which the molten metal is selected from the
15 group consisting of: iron; steel; aluminum.
5. The method claimed in claim 1, in which the said material is a blend which
includes strontium aluminate.
- 20 6. The method claimed in claim 5, in which the molten metal is selected from the
group consisting of: iron; steel; aluminum.
7. The method claimed in claim 5, in which said blend also contains silico-
aluminate.